Type Test Report

"1+" or "3" Notification No.: 1008

Test Report No.: **28240344 001** **Order No.:** **93356030** **Page 1 / 3**

Client: **JIANGSU ZHONGTIAN TECHNOLOGY CO., LTD.**

Harmonised standard: EN 50575:2014 + A1:2016
Classification standard: EN 13501-6:2014

Throughout this report a comma is used as the decimal separator.

Abbreviations: ***ok / P = passed***
fail / F = failed

www.tuv.hu

EN 60332-1-2

Clause	Requirement + Test	Result - Remark	Verdict
	ZTT GJFJV-4F 7.0mm (ZTT 0774)		
5	**Procedure**		
	Sample lenght (600 ± 25 mm).....:	615	P
	Approx. outer diameter (mm).....:	7,0	
	Flame application time (s).....:	60	P
6	**Evaulation of test results**		
	Not damaged area from lower edge of the top support (min. 50 mm).....:	337	P
	Damaged area from lower edge of the top support	495	P

Test Type: **Test for vertical flame propagation for a single insulated wire or cable**

1 kW pre-mixed flame

Standard: EN 50575:2014 + A1:2016, EN 13501-6:2014

EN 60332-1-2:2004 + A1:2015, EN 60332-1-1:2004 + A1:2015

No. of samples: 1

Ambient temperature: 26,5 °C

Date of test: 2017.08.07.

Classification according to EN 13501-6: E_{ca}

Photo documentation



Before test

After test

Measurin e ui ment list

Device	Manufacturer	Type	Identification No.	Next calibration
Measuring tape	Stabilo	RM 20W	502500	[redacted]

-END OF TEST REPORT-